

# Titan Top

## Dry-shake mineral aggregate surface hardener

**Titan Top is a ready to use product for hardening concrete floors.**

### USES

- Hardening indoor and outdoor concrete surfaces subject to light or moderate traffic.
- Applied over freshly levelled and floated concrete, this dry-shake surface hardener provides a low cost solution for hardening new industrial and commercial concrete floors.
- Areas where attractive, more uniform colour is desired to enhance the appearance of the floor and the working environment.
- Warehousing and storage areas, automotive maintenance areas and other maintenance facilities.

### ADVANTAGES

- A floor with increased strength and improved wear resistance.
- Contains special components that provide uniform density, and improve the properties of the finished floor surface.
- Up to twice the serviceable life of a plain concrete floor.
- High-density, easy to clean surface.

- More resistant to liquid penetration than plain concrete.
- Basically concrete coloured.
- Highly cost effective.
- A floor surface equal in performance to the natural product and available in several attractive colours.
- Specially designed, long lasting, light reflective properties that improve energy conservation and maximize the efficiency of existing or newly designed lighting systems.

### Typical properties

Colour	Natural or light concrete colours
MOH scale	7-8
Density	2,6 – 2,7
Aggregate grading value	18
Aggregate impact value	22
Abrasion value	2,5
Polished stone value	61
Storage life	Up to 12 months when stored in accordance with CLF



## COVERAGE

The standard application rate of Titan Top surface hardener is 5kg/m<sup>2</sup> of the floor area.

## METHOD OF APPLICATION

- Power floating is recommended.

## APPLICATION

- By power float.
- Do not apply over concrete containing more than 3% air.
- Do not cure coloured with salt water, brackish water, wet hessian, damp sand, plastic sheeting or ponding, use Aquacure.
- This product contains Portland cement which may cause irritation. Avoid contact with eyes and prolonged contact with skin.
- Do not apply over concrete containing free water on the surface.
- Do not add water for finishing purposes.

High air content makes proper application of dry shakes difficult or impractical, depending on the dimensions of the placement and ambient conditions.

This product should not be applied:

- Where operating and service conditions dictate the use of a metallic-aggregate surface hardener for greater wear resistance.
- For use in areas exposed to acids and their salts or to other materials known to rapidly attack or deteriorate Portland cement concrete unless coated with resin.

## CLEANING

Water before setting.

## PROTECTION ON COMPLETION

Cure only with Aquacure curing blankets. Coloured floors require extra care during installation, and must be protected from staining and damage after completion. Many factors can affect the final shade and appearance of a coloured concrete floor.

Burnishing can cause colour irregularity. Curing compounds wear off in time, but, in the case of coloured floor, if scratches or other marks on the curing compound are aesthetically unacceptable, the curing compound should be removed by means of a suitable solvent before using the floor, protect the surface against traffic and spillage until cured.

## TEMPERATURES AND RELATIVE HUMIDITY

As per concrete.

## MODEL SPECIFICATION

Non-metallic, dry shake, floor hardener.

## PACKAGING

Titan Top is supplied in 25kg polyethylene lined paper bags.

## HANDLING AND STORAGE

All Titan Top related products have a shelf life of 12 months if kept dry, cool store in the original, unopened packs. If stored at high temperatures and/or high humidity conditions, the shelf life may be reduced.

## HEALTH AND SAFETY

Avoid inhalation of dust and contact with skin and eyes. Suitable protective clothing, gloves, eye protection and respiratory protective equipment should be worn. The use of barrier creams provides additional skin protection. If contact with skin occurs, wash with water and soap. Splashes into eyes should be washed immediately with plenty of clean water and medical advice sought.

## IMPORTANT NOTE

This data sheet is issued as a guide to the use of the product(s) concerned. Whilst CLF endeavors to ensure that any advice, recommendation, specification or information is accurate and correct, the company cannot-because CLF has no direct or continuous control over where and how CLF products are applied- accept any liability either directly or indirectly arising from the use of CLF products, whether or not in accordance with any advice, specification, recommendation, or information given by the company.

## FURTHER INFORMATION

Where other products are to be used in conjunction with this material, the relevant technical data sheets should be consulted to determine total requirements. CLF has a wealth of technical and practical experience built up over the years in the company's pursuit of excellence in flooring and concrete technology.